

Kühlung

Toleranz e8

Beschichtung -

HA HB MTC UNI



Werkstoff / Material	Festigkeit / strength (N/mm ²)	Vc m/min	Ø 0,1 - 2		Ø 3 - 4		Ø 5		Ø 6		Ø 8		Ø 10		Ø 12		Ø 16		Ø 20			
			ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD	ae= 1xD	ae= 0,3xD
			ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	ap= 1xD	
			fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	
Stahl / Steel	< 850	45				0,022		0,027		0,032		0,042		0,055		0,065		0,08		0,09		
Stahl / Steel	< 1100	35				0,017		0,022		0,027		0,037		0,05		0,06		0,075		0,08		
Stahl / Steel	< 1400	25				0,012		0,017		0,022		0,032		0,045		0,05		0,065		0,075		
Gehärteter Stahl / Hardness Steel	< 55HRC																					
Gehärteter Stahl / Hardness Steel	< 60HRC																					
Gehärteter Stahl / Hardness Steel	< 67HRC																					
Gehärteter Stahl / Hardness Steel	≤ 70HRC																					
INOX	< 700	35				0,012		0,017		0,023		0,03		0,035		0,045		0,055		0,065		
INOX	< 850	30				0,01		0,014		0,02		0,025		0,028		0,035		0,045		0,055		
Guss / Castings		55				0,017		0,022		0,027		0,037		0,05		0,06		0,075		0,08		
Aluminium / Al		110				0,022		0,027		0,032		0,042		0,055		0,065		0,08		0,09		
Kupfer / Cooper																						
Kunststoffe / Plastics																						
Inconel																						
Titan / Titanium																						
Grafit / Graphite GFK / CFK																						

Bitte beachten, hierbei handelt es sich lediglich um Richtwerte! / Caution, these are only guide values!