

Kühlung 

Toleranz e8

Beschichtung TiSiN- α

HB ETC \neq  2xD  



Werkstoff / Material	Festigkeit / strength (N/mm ²)	Vc m/min	Ø 0,1 - 2		Ø 3 - 4		Ø 5		Ø 6		Ø 8		Ø 10		Ø 12		Ø 16		Ø 20			
			ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD	ae= 1xD	ae _{max} = 0,08xD
			ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}	ap= 1xD	ap= L2 _{max}
			fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)
Stahl / Steel	< 850																					
Stahl / Steel	< 1100	230							0,04		0,06		0,075		0,09		0,11		0,14			
Stahl / Steel	< 1400	180							0,015		0,03		0,045		0,05		0,07		0,1			
Gehärteter Stahl / Hardness Steel	< 55HRC																					
Gehärteter Stahl / Hardness Steel	< 60HRC																					
Gehärteter Stahl / Hardness Steel	< 67HRC																					
Gehärteter Stahl / Hardness Steel	≤ 70HRC																					
INOX	< 700	200							0,04		0,06		0,075		0,09		0,11		0,14			
INOX	< 850	190							0,04		0,06		0,075		0,09		0,11		0,14			
Guss / Castings																						
Aluminium / Al																						
Kupfer / Cooper																						
Kunststoffe / Plastics																						
Inconel																						
Titan / Titanium																						
Grafit / Graphite																						
GFK / CFK																						

Bitte beachten, hierbei handelt es sich lediglich um Richtwerte! / Caution, these are only guide values!