



















Kühlung 

Toleranz e8

Beschichtung TiAlN- α

HA HSC HPC  



Werkstoff / Material	Festigkeit / strength (N/mm ²)	Vc m/min	Ø 0,1 - 2		Ø 3 - 4		Ø 5		Ø 6		Ø 8		Ø 10		Ø 12		Ø 16		Ø 20			
																						
			ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD	ae= 0,3xD	ae= 0,05xD
			ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD	ap= L _{2max}	ap= 0,05xD
fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)		
Stahl / Steel	< 850	110	0,014	0,008	0,026	0,015	0,042	0,025	0,042	0,025	0,052	0,03	0,06	0,035	0,07	0,045	0,085	0,06	0,1	0,07		
Stahl / Steel	< 1100	80	0,014	0,008	0,026	0,015	0,042	0,025	0,042	0,025	0,052	0,03	0,06	0,035	0,07	0,045	0,085	0,06	0,1	0,07		
Stahl / Steel	< 1400																					
Gehärteter Stahl / Hardness Steel	< 55HRC																					
Gehärteter Stahl / Hardness Steel	< 60HRC																					
Gehärteter Stahl / Hardness Steel	< 67HRC																					
Gehärteter Stahl / Hardness Steel	≤ 70HRC																					
INOX	< 700	90	0,012	0,007	0,025	0,013	0,04	0,022	0,04	0,022	0,05	0,028	0,057	0,033	0,065	0,04	0,08	0,055	0,08	0,06		
INOX	< 850	85	0,012	0,007	0,025	0,013	0,04	0,022	0,04	0,022	0,05	0,028	0,057	0,033	0,065	0,04	0,08	0,055	0,08	0,06		
Guss / Castings		100	0,014	0,008	0,026	0,015	0,042	0,025	0,042	0,025	0,052	0,03	0,06	0,035	0,07	0,045	0,085	0,06	0,1	0,07		
Aluminium / Al																						
Kupfer / Cooper																						
Kunststoffe / Plastics																						
Inconel																						
Titan / Titanium																						
Grafit / Graphite																						
GFK / CFK																						

Bitte beachten, hierbei handelt es sich lediglich um Richtwerte! / Caution, these are only guide values!

