

K203001 | VHM Vollradiusfräser SC Full Radius Cutter

Kühlung	
Toleranz	f7
Beschichtung	-



Werkstoff / Material	Festigkeit / strength (N/mm ²)	Vc m/min	Ø 0,1 - 2	Ø 3 - 4	Ø 5	Ø 6	Ø 8	Ø 10	Ø 12	Ø 16	Ø 20	
			ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD	ae= 0,05xD
			ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD	ap= 0,05xD
			fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	
Stahl / Steel	< 850	80	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Stahl / Steel	< 1100	50	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Stahl / Steel	< 1400											
Gehärteter Stahl / Hardness Steel	< 55HRC											
Gehärteter Stahl / Hardness Steel	< 60HRC											
Gehärteter Stahl / Hardness Steel	< 67HRC											
Gehärteter Stahl / Hardness Steel	≤ 70HRC											
INOX	< 700	45	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
INOX	< 850	40	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Guss / Castings		75	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Aluminium / Al		190	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Kupfer / Cooper		170	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Kunststoffe / Plastics		240	0,008	0,015	0,03	0,045	0,06	0,07	0,08	0,09		
Inconel												
Titan / Titanium												
Grafit / Graphite GFK / CFK												

Bitte beachten, hierbei handelt es sich lediglich um Richtwerte! / Caution, these are only guide values!