









K207038 | VHM Stirntorusfräser SC Face Torus Cutter

Kühlung	
Toleranz	h9
Beschichtung	TiSiN- α



Werkstoff / Material	Festigkeit / strength (N/mm ²)	Vc m/min	Ø 0,1 - 2	Ø 3 - 4	Ø 5	Ø 6	Ø 8	Ø 10	Ø 12	Ø 16	Ø 20	
												
			ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD	ae= 1xD
			ap _{max} = 0,15mm	ap _{max} = 0,2mm	ap _{max} = 0,25mm	ap _{max} = 0,4mm	ap _{max} = 0,5mm	ap _{max} = 0,75mm	ap _{max} = 0,8mm	ap _{max} = 1mm	ap _{max} = 1mm	ap _{max} = 1mm
			fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)	fz (mm/Z)
Stahl / Steel	< 850											
Stahl / Steel	< 1100											
Stahl / Steel	< 1400											
Gehärteter Stahl / Hardness Steel	< 55HRC											
Gehärteter Stahl / Hardness Steel	< 60HRC											
Gehärteter Stahl / Hardness Steel	< 67HRC											
Gehärteter Stahl / Hardness Steel	≤ 70HRC											
INOX	< 700											
INOX	< 850											
Guss / Castings												
Aluminium / Al												
Kupfer / Cooper												
Kunststoffe / Plastics												
Inconel												
Titan / Titanium		100	0,02	0,055	0,065	0,075	0,09	0,12	0,16	0,2		
Grafit / Graphite												
GFK / CFK												

Bitte beachten, hierbei handelt es sich lediglich um Richtwerte! / Caution, these are only guide values!